



IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicants : Eric Wolfsgruber et al. Confirmation No.: 3047
Serial No. : 10/057,547
Filed : January 25, 2002
TC/A.U. : 1775
Examiner : John J. Zimmerman

Docket No. : 02-121
Customer No.: 34704

DECLARATION UNDER 37 C.F.R. 1.132

I, Dr. Eric Wolfsgruber declare as follows:

That, I am a co-inventor of U.S. Patent Application Serial
No.09/647,411.

That, I am a graduate of the University of Technology of Vienna,
Austria, where I received a doctorate degree in Technical
Chemistry in 1997.

That, from 1997 to the present I have been employed at MEPURA.

The following data establishes the superiority of powder
metallurgically produced metal foam of the present invention.

Two AlSi12 foams were prepared as follows:

FOAM A from molten metal per VALDO '666

AlSi12 was molten in an electrical furnace at approx. 600°C. 1%
of a foaming agent (TiH₂-powder) was poured in the melt, after
decomposition of the foaming agent the melt was poured into a
mould having the shape of a hollow cylinder and cooled rapidly.
The resulting foam is FOAM A.

Not considered - assigned 50/9/05



Mepura Metallpulver Gesellschaft m.b.H. • Lach 22 • A - 5282 Ranshofen/ Austria



MEPURA Metallpulver
Gesellschaft m.b.H.

Lach 22
5282 Ranshofen
Austria

Tel.: (+43) (7722) 62216-0
Fax: (+43) (7722) 62216-11
E-Mail: office@mepura.at

13.06.2005

Application: 10/057,547

DECLARATION UNDER 37 C.F.R. 1.132

I, Dr. Eric Wolfgruber declares as follows:

That, I am a co-inventor of U.S. Patent Application Serial No.09/647,411

That, I am a graduate of the University of Technology of Vienna, Austria, where I received a doctorate degree in Technical Chemistry in 1997.

That, from 1997 to the present I have been employed at MEPURA.

The following text data shall establish the superiority of powder metallurgically produced metal foam.

Two AlSi12 foams were prepared as follows:

Alloy A – Foam:

AlSi12 was molten in an electrical furnace at approx. 600°C. 1% of a foaming agent (TiH₂-powder) was poured in the melt, after decomposition of the foaming agent the melt was poured into a mould having the shape of a hollow cylinder and cooled rapidly. The resulting foam is Foam A.

Composite B – Foam:

Al + 10 - 12% Si powder with a grain size of 0 – 500 µm as well as 1% foaming agent (TiH₂-powder) have been admixed thoroughly and compressed in a die. The pressed densified material was placed into a heatable mould.(shape of a hollow cylinder) and shortly heated up

Bankverbindungen:

Oberbank AG Braunau am Inn
BLZ: 15040 Kto: 201-0486/00
IBAN: AT76 1504 0002 0104 8600
BIC: OBKAT2L

Salzburger Sparkasse Braunau
BLZ 20404 Kto: 06605015003
IBAN: AT13 2040 4068 0501 5003
BIC: SBGSAT2S

Bank Austria Creditanstalt Salzburg
BLZ: 12000 Kto: 800-144991/00
IBAN: AT08 1200 0800 1449 9100
BIC: BKAUATWW

Oberbank AG München
BLZ: 70120700 Kto: 1001192440
IBAN: DE12 7012 0700 1001 1924 40
BIC: OBKLEDEM

Raiffeisen-Landesbank O.Ö. Linz
BLZ 34000 Kto: 1 144 344
IBAN: AT83 3400 0000 0114 4344
BIC: RZ00AT2L

MEPURA Metallpulver
Gesellschaft m.b.H. Ranshofen
Lach 22
5282 Ranshofen/Austria

HRB 33 Ried im Innkreis
Firmenbuch-Nr. 110253 m
UID-Nr. ATU 21671705

Geschäftsführer:
Gen. Rohrseitz
Walter Rajner

Considered - 11/9/05